



21042 CARONNO PERTUSELLA (Va) - Via Trieste 285 - Tel. 029650607 - Fax 029659754

www.lakplaster.it - e-mail: info@lakplaster.it

DATA SHEET

MILLEUSI

PROFESSIONAL GLOSS ENAMEL

Field of use

Synthetic enamel based on special glycerophthalic resins, with good brushability, flow, brilliance, and excellent resistance to bad weather. **A THOUSAND** is particularly suitable for "do it yourself" and for any external construction, industrial and domestic work, for which excellent aesthetic characteristics and durability are required outdoors.

Particularly suitable for wooden doors and windows and iron products (painting on the outside of poles and tank fences, pylons, shutters and carpentry).

Colors

Color chart, Ral colors, sample colors

Preparation of the product

Mix thoroughly until uniform consistency before dilution.

Appearance of the film

Brilliant gloss, gloss > 90 a (60 ° reading angle)

Dilution

For brush / roller applications: 10 - 20% with synthetic thinner

For spray applications : 20 - 25% with nitro thinner

TECHNICAL FEATURES

Physical characteristics

Specific weight	1,050 - 1,220 kg / l second color
Visc. Ford 4/20 ° C	130 - 150 seconds
Flash point closed)	> 21 ° C (Abel Pensky cup)

Theoretical yield

30 microns dry	13 - 15	sqm / kg
""	12 - 17	sqm / l

Drying

Dust dry	12 hours
Dry to the touch	6 - 8 hours
Deep	18 - 20 hours
Recoatible	18 - 20 hours

