



Lak Plaster®
PITTURE E VERNICI



21042 CARONNO PERTUSELLA (Va) - Via Trieste 285 - Tel. 029650607 - Fax 029659754

www.lakplaster.it - e-mail: info@lakplaster.it

DATA SHEET

AZETA

WASHABLE INTERNAL EXTERNAL WATER-BASED PAINT FOR DRYWALL AND MULTIPURPOSE

Features

: Civil plaster, prefabricated panel, gypsum and plasterboard (new):
If the substrates listed above are not particularly absorbent, apply one or two coats of Azeta directly.

Previously painted interior walls:

remove the parts with poor adhesion from the surface, level it with putty in paste or powder from the Lak Plaster range. Be careful to sand until completely level and clean up from dust.

If the substrates are particularly absorbent, it is recommended to pre-treat the surface with ISOLAK acrylic fixative (strong penetration).

Internal walls treated with water-based paint:

Thoroughly clean the surface after having leveled it with paste or powder fillers from the Lak Plaster range.

Apply directly one or two coats of AZETA for complete coverage.

Principles of photocatalysis

: In the formula, thanks to the use of titanium dioxide which, subjected to sunlight, the molecules of pollutants are transformed into substances harmless to health, and the process is also activated in the presence of artificial light.

Practical advice

: It is advisable during the application not to interrupt the work if the wall has not been finished.

Ambient conditions between 5 ° C and 35 ° C

Support conditions between 5 ° C and 35 ° C

humidity <80%

The product does not guarantee ease of application if not diluted correctly.

Binder

: Mix of acrylic copolymers

Appearance

: Opaque - Antiglare

Washability

: After 48 hours. 10,000 Brush Strokes



Lak Plaster®
PITTURE E VERNICI



21042 CARONNO PERTUSELLA (Va) - Via Trieste 285 - Tel. 029650607 - Fax 029659754

www.lakplaster.it - e-mail: info@lakplaster.it

DATA SHEET

Specific weight	: 1,500 - 1,600 kg / lt
Viscosity at 20 ° C	: 8,000 - 14,000
Surrender	: <u>Perfect fit</u> : dilution with water 10 -20% by volume 9 m2 (2 hands) <u>By roller</u> : dilution with water 10 -20% by volume 9 m2 (2 coats): <u>Spray</u> dilution with water 20% by volume 12 m2 (1 coat)
Color	:White
Drying	: To the touch : 40 minutes Overlap : 6 hours
VOC classification (Directive 2004/42 / EC)	: EU limit value for this product (Cat A / a): 30 g / l (2010): This product contains a maximum of 30 g / l VOC